

FIBERSTRAND 150ML

POLYPROPYLENE MICRO-FIBER

FIBERSTRAND
fibers

DESCRIPTION

FIBERSTRAND 150ML is a multi-length, monofilament polypropylene micro-fiber for concrete reinforcement that complies with ASTM C 1116, Standard Specification for Fiber Reinforced Concrete and Shotcrete, and is specifically designed to help mitigate the formation of plastic shrinkage cracking in concrete. Typically used at a dosage rate of 0.67 lbs/yd (0.4 kg/m³), FIBERSTRAND 150ML fibers have been shown to reduce plastic shrinkage cracking by as much as 76% when compared to plain concrete. FIBERSTRAND 150ML fibers also comply with applicable portions of the International Code Council (ICC) Acceptance Criteria AC308 for synthetic fibers.

PRIMARY APPLICATIONS

- Flatwork for industrial, commercial and residential concrete projects
- Footings, foundations, walls and tank applications
- Concrete pipe, vault structures and pre-cast / pre-stressed beams

FEATURES/BENEFITS

- Controls and mitigates plastic shrinkage cracking
- Reduces segregation and bleed-water
- Provides three-dimensional reinforcement against micro-cracking
- Increases surface durability
- Reduction of in-place cost versus wire mesh for temperature / shrinkage crack control
- Easily added to concrete mixture at any time prior to placement

TECHNICAL INFORMATION

Typical Engineering Data

Material..... monofilament polypropylene
Specific Gravity 0.91
Typical dosage rate 0.67 lb/yd (0.4 kg/m³)
Available lengths: standard blend of ¼" (6 mm),
½" (12 mm) and ¾" (19 mm)
Tensile Strength..... 97 ksi (660 MPa)
Modulus of Elasticity 580 ksi (4.0 GPa)
Melt point..... 330°F (165°C)
Electrical Conductivity..... low
Water absorption..... negligible
Acid and Alkali Resistance..... excellent
Fiber count approx. 54 million / lb (0.45 kg)

PACKAGING

FIBERSTRAND 150ML fibers are packaged in 0.67 lb (0.3 kg), 1.0 lb (0.45 kg), and 5.0 lb (2.27 kg) water soluble bags.

SHELF LIFE

3 years in original, unopened package.

DIRECTIONS FOR USE

FIBERSTRAND 150ML fibers can be added to the concrete mixture at any time prior to placement of the concrete. It is generally recommended to add any fiber material at the ready-mix concrete plant during batching. Fibers must be mixed with concrete for a minimum of three (3) minutes at maximum mixing speed to ensure complete dispersion and uniformity.

FIBERSTRAND 150ML
Polypropylene Micro-fiber

Master Format #: 03 2400

Revised: 2.07



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110
Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596
www.euclidchemical.com

An **RPM** Company



CLEAN-UP

Loose fiber material may be disposed in proper receptacles for refuse. Finishing equipment with fibers embedded in concrete should be thoroughly cleaned.

PRECAUTIONS/LIMITATIONS

- Use of fibers may cause an apparent loss in measured slump of concrete. This may be offset with the use of a water reducing admixture if necessary.
- Fibers should never be added to a “zero-slump” concrete. Ensure a minimum concrete slump of 3” (80 mm) prior to addition of any fiber material. Fibers may also be added in loose form to aggregate charging devices.
- In all cases, consult the Material Safety Data Sheet before use.

WARRANTY: The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.